

재활용 폐기물 반입현황 (2015년 하반기)

□ 업체명 : 라파즈하라시엔트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계 (7~12월)	분석결과										
	대분류	중분류	세분류			Pb	Cu	Cd	As	Hg	Cl	저위발열량	분석일자			
						(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(%)	(kcal/kg)				
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수오니	A	3,006	6.4	135.7	11.2	14.5	0.8	-	-	11/26			
				B	457	23.3	256.4	6.2	10.4	0.1	-	-	11/26			
				C	687	49.3	112.3	6.3	31.3	0.3	-	-	8/19			
				D	257	14.3	236.1	15.3	33.0	0.2	-	-	8/19			
				E	613	45.6	473.3	18.4	25.1	0.2	-	-	11/26			
		하수처리오니 (51-01-04)	하수오니	A	4,380	22.3	452.5	1.7	3.9	0.1	-	-	11/25			
				B	124	21.4	326.5	22.1	15.3	0.1	-	-	11/27			
				C	83	95.6	248.5	16.3	6.2	0.0	-	-	7/31			
				D	1,068	84.6	156.2	6.4	31.2	0.5	-	-	7/24			
				E	386	84.1	321.5	2.4	12.5	0.4	-	-	7/31			
				F	314	65.2	241.0	22.9	24.5	0.4	-	-	11/27			
				G	233	28.8	259.7	1.2	6.3	0.7	-	-	7/31			
				H	11,433	9.7	346.4	0.4	1.4	-	-	-	11/25			
				I	2,562	35.1	236.5	25.6	24.6	0.6	-	-	7/31			
				J	2,404	66.3	542.2	5.2	12.1	0.2	-	-	11/27			
	유기성오니			A	67	23.7	239.5	28.4	12.3	0.4	-	-	10/30			
				A	74,360	9.9	10.4	0.3	2.2	0.0	-	-	7/25			
				B	10,016	42.1	241.5	24.2	15.7	0.4	-	-	7/25			
				A	180	-	7.1	0.2	-	0.0	-	-	12/29			
				B	4,428	7.0	8.6	0.1	5.7	0.0	-	-	11/11			
	무기성오니류 (51-02-00)	공정오니 (51-02-02)	공정오니	C	22,009	1.8	9.7	-	-	0.3	-	-	11/3			
				A	717	21.4	15.3	7.2	7.3	0.8	-	-	11/27			
				A	8,691	-	6.6	0.4	0.7	-	-	-	10/13			
	광재류 (51-04-00)	제강 슬래그 (51-04-02)	제강 슬래그	A	168	3.8	50.2	1.5	4.7	0.0	-	-	7/25			
				A	3,748	0.7	30.8	0.1	1.0	0.0	-	-	12/21			
	폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	B	18,664	3.5	101.3	0.4	2.6	-	-	-	11/10			
				C	1,370	5.1	62.5	0.2	0.7	0.0	-	-	9/10			
				D	5,142	23.2	66.5	0.2	-	0.0	-	-	11/10			
				A	17,147	21.8	46.1	0.4	3.7	0.3	-	-	11/1			
	연소잔재물 (51-13-00)		석탄재	B	70,122	8.5	27.1	0.1	12.3	-	-	-	7/6			
				C	30,634	3.4	24.0	0.0	12.5	-	-	-	11/28			
				D	7,839	6.9	29.3	0.1	20.6	0.3	-	-	11/13			
				E	3,900	-	16.4	0.1	1.9	-	-	-	12/21			
				A	637	73.1	30.1	6.5	6.5	0.3	-	-	11/27			
	보조 원료	폐합성고분자화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	313	2.6	149.3	-	1.4	-	0.7	5,793	10/27-11/2		
					B	1,861	58.3	156.8	2.6	0.4	-	0.8	4,774	10/20-10/26		
					C	179	43.8	39.7	0.6	5.7	0.1	1.5	4,640	10/6-10/12		
					D	42	31.6	43.7	1.9	2.7	-	1.1	6,493	11/24-11/30		
					E	1,865	21.3	31.1	0.5	-	0.0	1.1	5,182	10/27-11/2		
					F	4,041	17.5	94.2	0.4	2.1	-	0.8	4,924	10/20-10/26		
					G	276	30.5	57.3	3.7	0.8	-	0.6	5,808	10/20-10/26		
					H	11,008	122.5	287.1	8.9	3.9	-	0.8	4,862	9/1-9/7		
					I	2,705	18.1	36.2	0.4	-	0.2	0.9	4,665	9/22-9/28		
					J	338	107.5	90.7	5.1	0.3	0.0	1.3	4,839	7/21-7/27		
					K	1,013	57.5	188.3	-	3.3	-	1.2	6,365	10/6-10/12		
L					4,695	27.5	179.3	0.7	-	-	0.7	6,212	10/20-10/26			
M					1,172	70.4	133.4	5.4	-	-	0.9	4,626	10/20-10/26			
N					1,686	60.1	117.1	0.5	2.2	0.0	1.2	5,275	10/20-10/26			
O					2,359	54.2	71.5	0.9	-	-	0.5	5,006	10/20-10/26			
P					520	34.9	60.2	1.9	1.1	-	1.9	5,282	11/24-11/30			
Q					4,274	2.8	6.6	3.0	-	-	0.7	5,691	10/20-10/26			
R					1,336	92.1	218.6	5.1	1.7	-	1.0	4,973	8/11-8/17			
S					439	36.9	70.6	2.7	-	-	0.1	5,904	11/24-11/30			
T					2,908	104.6	707.4	3.2	1.9	-	0.7	4,685	10/6-10/12			
U					3,841	34.5	61.1	0.5	-	-	0.6	5,290	10/20-10/26			
V					2,069	61.2	241.8	1.1	0.2	-	1.9	4,714	11/24-11/30			
W					1,547	32.2	136.5	1.8	-	-	0.5	4,718	10/20-10/26			
X					13,586	77.3	75.7	1.6	3.0	-	0.5	6,003	10/6-10/12			
Y					298	91.2	118.7	0.2	-	-	0.6	5,213	9/29-10/5			
Z					418	89.3	119.2	3.4	4.2	0.5	0.4	4,684	9/29-10/5			
AA					257	69.3	173.2	2.1	0.1	0.0	0.9	5,550	8/11-8/17			
AB					11	160.0	38.5	0.2	-	0.0	1.9	5,801	11/10-11/16			
AC					80	29.1	97.1	-	0.5	-	0.8	4,633	10/20-10/26			
폐합성고무류 (51-03-02)					폐고무	A	228	20.6	21.4	0.4	-	0.4	6,612	7/21-7/27		
						B	28	16.1	27.2	0.2	-	1.8	5,378	7/21-7/27		
페타이어 (51-15-00)						페타이어	A	1,069	21.4	22.2	0.3	0.7	-	0.3	7,276	10/20-10/26
							B	474	30.2	11.0	0.9	0.2	0.0	0.3	5,003	11/10-11/16
							C	2,925	19.0	5.2	1.9	0.1	-	0.2	5,086	10/20-10/26
							D	1,557	51.6	72.5	0.7	2.4	0.0	0.2	6,970	10/20-10/26
폐목재류 (51-20-00)			폐목재류	A	223	18.4	8.4	1.4	-	-	0.4	3,831	10/20-10/26			
				B	1,420	21.9	10.8	0.1	-	-	0.2	4,052	9/22-9/28			
				C	1,127	11.4	7.5	1.1	1.0	0.0	0.2	3,740	9/22-9/28			
				D	2,920	23.4	3.4	1.7	0.6	0.0	0.4	3,632	9/22-9/28			
				E	902	10.8	37.2	0.4	-	-	0.3	3,880	8/11-8/17			
				F	499	14.4	13.2	0.5	0.9	0.0	0.3	3,631	11/24-11/30			
				G	1,223	24.4	8.0	1.5	-	-	0.3	4,280	10/20-10/26			
				H	18,761	11.2	14.2	1.6	-	-	0.2	3,686	9/22-9/28			
				I	2,636	2.3	20.3	0.1	-	-	0.3	4,125	9/22-9/28			
분진 (51-05-00)			중유회	A	835	7.8	49.7	0.2	10.6	0.1	0.1	6,349	11/17			
	B			2,135	0.9	44.9	0.1	10.7	0.1	0.2	6,690	8/14				