

재활용 폐기물 반입현황 (2016년 상반기)

□ 업체명 : 한라시멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계(1-6월)	분석결과							
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수오니	A	3,918	1.6	182.2	22.3	16.1	0.0	-	-	4/29
				B	1,432	-	259.5	5.6	45.5	-	-	-	4/29
				C	2,353	1.9	45.9	-	-	-	-	-	4/15
				A	4,198	2.4	250.2	35.5	15.5	0.0	-	-	3/17
				B	127	19.5	82.1	10.2	4.2	0.0	-	-	4/15
				C	74	32.5	41.3	2.2	6.7	0.0	-	-	4/15
		하수처리오니 (51-01-04)	하수오니	D	1,514	9.6	212.5	1.1	6.5	0.0	-	-	4/15
				E	10,439	6.1	347.0	0.6	5.8	0.0	-	-	1/11
				F	3,206	8.7	117.8	1.2	1.7	0.0	-	-	4/15
				G	748	131.7	188.0	1.7	2.5	-	-	-	4/15
				H	1,804	20.0	398.2	2.6	35.7	0.0	-	-	3/4
				I	659	125.0	431.3	21.5	22.3	0.0	-	-	3/4
				J	12	49.5	205.9	34.3	15.4	0.0	-	-	1/19
				K	1,103	12.5	465.0	4.1	14.9	-	-	-	4/15
				L	1,114	98.0	228.4	10.5	17.9	0.5	-	-	5/23
				M	486	133.2	425.4	1.0	4.9	0.2	-	-	4/14
				N	19	146.2	356.2	0.2	1.1	0.1	-	-	4/14
				O	129	10.2	124.0	3.7	12.2	0.3	-	-	4/14
	P	16	132.1	490.0	8.3	-	0.0	-	-	4/14			
				유기성오니	A	48	91.0	289.8	2.0	2.7	-	-	2/2
	무기성오니류 (51-02-00)	폐수처리오니 (51-02-01)	폐수오니	A	62,589	10.9	9.9	0.1	3.2	0.0	-	-	4/27
				B	7,055	7.3	19.1	0.2	-	-	-	5/12	
				A	3,508	31.4	18.0	1.7	11.7	0.0	-	5/12	
		공정오니 (51-02-02)	공정오니	B	4,270	2.0	42.2	8.1	12.6	-	-	5/12	
				C	25,817	0.4	7.5	-	0.9	0.0	-	2/3	
				A	631	23.6	31.3	0.1	33.9	0.0	-	1/19	
	정수처리오니 (51-02-03)	정수오니	A	631	23.6	31.3	0.1	33.9	0.0	-	1/19		
	광재류 (51-04-00)	제강 슬래그 (51-04-02)	제강 슬래그	A	12,214	-	7.4	0.3	-	-	-	5/16	
	폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	3,366	1.9	39.1	0.2	3.3	0.0	-	6/7	
				B	23,923	10.5	219.3	0.1	-	0.0	-	6/14	
C				2,156	0.1	44.7	-	5.2	0.0	-	2/3		
D				117	0.5	58.2	0.1	3.2	-	-	6/30		
E				1,830	8.1	52.7	0.5	5.6	-	-	1/14		
폐석고 및 폐석회 (51-12-00)	폐석고 (51-12-01)	폐석고	A	58	19.3	29.6	0.1	0.6	0.0	-	4/14		
연소잔재물 (51-13-00)		석탄재	A	24,469	15.0	25.8	0.9	11.5	0.6	-	1/18		
			B	55,115	4.9	23.9	0.2	10.5	0.1	-	2/15		
			C	9,674	10.6	29.6	0.3	10.2	0.0	-	2/20		
			D	6,651	12.1	46.2	0.4	16.1	0.3	-	1/27		
			E	7,793	0.5	27.9	0.1	3.9	0.0	-	3/14		
보조 원료	폐합성고분자화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	235	29.8	172.0	1.5	1.2	-	0.6	4,990	3/7-14
				B	2,950	20.8	141.1	0.6	-	-	0.4	5,620	5/10-16
				C	1,332	9.1	33.6	-	0.5	0.0	1.2	4,547	5/10-16
				D	127	11.5	193.6	6.2	11.0	-	0.7	6,259	6/21-6/27
				E	3,086	9.7	52.4	0.1	1.7	-	0.8	6,488	1/5-11
				F	6,293	45.7	253.8	0.3	0.6	-	0.6	4,729	5/10-16
				G	88	5.4	30.0	-	2.5	-	0.7	5,551	5/24-30
				H	6,356	121.4	205.0	1.2	-	0.0	1.2	5,581	3/7-14
				I	1,924	71.3	94.2	1.5	-	-	0.9	5,620	5/10-16
				J	126	82.5	173.2	1.6	0.1	-	1.0	5,338	3/8-3/14
				K	4,896	19.6	51.1	2.4	-	-	1.9	6,230	1/19-25
				L	161	25.9	129.9	0.8	2.2	0.0	1.1	4,658	1/19-25
				M	464	14.1	174.5	1.2	0.6	-	1.2	6,115	1/19-25
				N	2,025	4.8	40.1	4.0	-	-	0.7	6,312	3/17-21
				O	625	179.1	783.9	7.6	1.2	0.0	1.3	4,666	2/11-15
				P	4,737	4.3	22.3	-	0.4	-	0.2	4,658	1/5-11
				Q	129	9.8	62.0	0.2	-	-	0.1	4,631	1/26-2/1
				R	1,690	29.6	122.4	0.9	2.6	-	0.1	5,174	1/26-2/1
				S	180	13.2	21.3	1.1	4.5	-	0.7	4,836	6/7-6/13
				T	3,603	24.1	35.3	0.4	4.5	-	0.7	5,297	3/17-21
	U	1,197	57.7	481.9	1.7	1.5	-	0.6	4,633	2/16-22			
	V	15,224	45.0	46.9	2.3	1.9	-	0.4	6,700	3/17-21			
	W	2,825	98.9	149.9	7.9	7.0	-	1.4	4,615	3/7-14			
	X	227	167.0	66.6	1.7	0.6	-	0.7	4,740	5/10-16			
	페타이어 (51-15-00)		페타이어	A	260	35.2	12.0	8.0	0.2	0.0	0.4	4,679	5/10-16
				B	1,744	146.3	245.1	1.7	12.2	-	0.5	4,831	5/10-16
				C	1,220	129.9	88.4	5.0	0.1	0.0	0.3	4,911	5/10-16
페목재류 (51-20-00)		페목재류	A	980	20.7	25.2	1.3	1.9	-	0.6	3,780	5/10-16	
			B	1,055	16.5	13.0	0.4	-	-	0.3	3,914	3/7-14	
			C	1,745	1.9	7.6	0.3	1.2	0.0	0.3	4,098	3/7-14	
			D	1,104	15.0	12.8	0.1	-	0.1	0.3	4,067	5/10-16	
			E	14,745	23.9	23.6	1.7	-	-	0.2	3,741	3/7-14	
			F	587	11.2	24.2	1.1	1.0	-	0.1	4,039	6/21-6/27	
			G	6,247	7.2	23.3	0.3	1.2	-	0.2	4,036	5/10-16	
분진 (51-05-00)		중유회	A	1,619	13.2	28.8	4.1	-	0.0	0.1	5,953	4/25	
			B	2,493	36.8	76.1	1.3	1.1	-	0.4	4,908	4/11	