

재활용 폐기물 반입현황 (2016년 하반기)

□ 업체명 : 한라시멘트(옥계공장)

구분	종류		공급자	반입량 (톤) 누계(7~12월)	분석결과							
	대분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자
대체 원료	유기성오니류 (51-01-00)	폐수오니	A	3,018	3.9	212.6	25.9	7.4	-	-	-	10/4
			B	1,054	-	203.6	6.2	12.1	0.0	-	-	10/5
			C	1,857	-	47.5	-	-	-	-	-	12/5
		하수오니	A	4,766	21.4	403.9	1.3	6.2	0.0	-	-	12/5
			B	147	18.6	76.2	4.5	2.7	0.0	-	-	8/1
			C	94	23.8	81.6	2.4	0.8	0.0	-	-	9/9
			D	1,216	4.3	100.7	3.3	1.8	0.1	-	-	10/4
			E	8,571	6.2	335.2	0.7	3.9	0.0	-	-	12/5
			F	2,944	9.5	456.4	1.2	1.7	0.0	-	-	10/6
			G	1,955	10.6	335.1	0.7	6.2	0.0	-	-	12/5
			H	984	18.4	121.8	0.5	1.4	0.0	-	-	12/14
			I	43	5.7	62.4	0.5	3.1	0.0	-	-	7/13
			J	118	7.8	80.9	1.6	2.2	0.0	-	-	7/5
			K	1,020	13.8	91.6	2.6	1.4	0.0	-	-	9/14
			L	2,776	12.2	289.0	1.1	2.8	0.0	-	-	10/2
			M	161	10.3	105.6	0.9	1.7	0.0	-	-	10/5
			N	655	102.0	159.6	2.6	8.8	0.0	-	-	10/5
			O	40	20.8	77.9	1.8	1.0	0.0	-	-	8/9
	무기성오니류 (51-02-00)	폐수오니	A	85,115	4.6	9.8	0.1	2.9	-	-	-	8/19
			B	7,334	5.8	13.2	0.1	2.1	0.0	-	-	9/7
		공정오니	A	29	2.6	11.4	0.2	3.0	0.0	-	-	7/1
			B	2,052	0.2	10.5	-	1.2	-	-	-	12/8
			C	13,839	7.7	9.9	0.1	3.9	0.0	-	-	7/29
		정수오니	A	818	24.3	11.2	0.2	7.4	0.0	-	-	8/16
	광재류 (51-04-00)	제강 슬래그	A	255	-	5.9	1.0	0.5	-	-	-	7/25-31
	폐주물사 및 폐사 (51-06-00)	폐주물사	A	3,595	2.6	21.3	0.1	1.4	-	-	-	11/9
			B	24,523	8.6	307.0	0.2	-	0.0	-	-	8/16
C			138	25.4	177.1	0.7	6.4	0.0	-	-	12/26	
D			223	15.1	120.5	1.0	0.1	0.0	-	-	7/14	
E			6,138	-	84.1	0.4	4.5	-	-	-	11/3	
폐석고 및 폐석회 (51-12-00)	폐석고	A	29,433	1.9	3.0	-	-	1.0	-	-	9/25	
연소잔재물 (51-13-00)	석탄재	A	12,446	7.2	19.1	0.5	14.4	0.2	-	-	8/2	
		B	56,944	10.7	33.9	0.1	3.4	0.1	-	-	10/22	
		C	25,907	4.9	28.4	0.1	17.3	0.0	-	-	12/7	
		D	6,250	2.7	26.2	0.1	11.0	0.2	-	-	11/22	
		E	3,988	5.3	29.9	-	13.8	0.1	-	-	8/23	
		F	5,100	6.7	32.0	0.1	7.8	0.1	-	-	12/25	
보조 원료	폐합성고분자화합물 (51-03-00)	폐합성수지	A	28	16.2	32.3	1.8	0.5	0.0	0.8	5,607	9/6-9/12
			B	6,775	7.9	28.5	-	-	0.0	0.5	4,530	8/23-29
			C	2,050	7.0	97.4	-	2.4	0.0	0.5	4,700	10/25-31
			D	1,121	38.8	417.5	-	0.7	-	0.6	6,237	8/23-29
			E	4,308	15.3	26.0	0.0	-	-	0.5	4,572	8/23-29
			F	7,942	29.4	48.8	1.7	0.5	0.0	0.8	5,238	8/23-29
			G	248	45.3	90.3	0.1	3.5	-	1.9	4,711	11/22-28
			H	510	29.5	523.6	0.1	-	0.0	0.6	6,083	11/1-7
			I	2,110	179.7	106.0	1.0	3.2	-	1.0	5,224	10/25-31
			J	498	91.2	156.0	0.7	0.6	0.0	0.6	6,534	10/25-31
			K	4,755	59.0	219.0	6.8	-	0.0	1.0	5,120	10/25-31
			L	126	21.4	184.2	1.3	1.1	0.0	0.6	4,536	12/20-26
			M	2,860	26.0	48.2	0.2	1.8	0.0	0.5	6,644	8/23-29
			N	3,714	20.1	9.4	-	1.1	-	0.2	6,429	10/25-31
			O	12	86.4	18.1	0.1	0.9	0.0	0.7	6,346	12/27-30
			P	23	9.8	12.5	0.1	-	0.0	0.1	4,527	11/8-14
			Q	251	47.0	66.2	1.6	0.1	0.0	0.4	4,842	12/20-26
			R	53	19.5	26.9	0.6	0.3	0.0	0.1	5,599	12/27-30
			S	54	1.6	2.1	-	-	0.0	0.1	5,916	8/23-29
			T	279	36.5	65.3	0.5	-	0.0	1.4	5,098	12/20-26
	U	3,826	19.6	85.2	1.1	1.5	0.0	0.7	6,932	11/1-7		
	V	1,474	45.9	396.4	1.1	-	0.0	0.4	5,062	7/5-11		
	W	19,472	38.2	41.8	0.3	1.5	0.0	0.6	7,147	10/25-31		
	X	1,715	39.4	44.1	0.2	-	0.1	0.2	4,594	8/23-29		
	Y	48	148.0	115.5	1.6	-	-	1.6	4,590	8/23-29		
	페타이어 (51-15-00)	페타이어	A	160	32.8	85.2	0.8	1.0	0.0	0.4	4,991	8/23-29
			B	915	10.9	67.3	0.3	0.5	0.1	0.2	4,615	11/1-7
C			673	43.2	44.1	0.2	1.9	0.0	0.7	4,592	11/22-28	
폐목재류 (51-20-00)	폐목재류	A	1,410	21.6	20.2	0.2	1.0	-	0.2	3,716	7/5-11	
		B	445	20.0	15.5	1.5	0.2	0.0	0.3	3,771	12/20-26	
		C	924	7.8	8.4	0.4	0.8	-	0.1	3,957	7/12-18	
		D	1,188	1.2	5.3	0.1	1.8	0.0	0.1	3,716	7/5-11	
		E	16,450	8.5	9.8	1.1	1.2	-	0.1	3,967	7/5-11	
		F	3,348	22.7	15.9	1.4	-	0.0	0.5	3,723	12/20-26	
		G	2,239	5.4	6.2	0.2	-	0.0	0.1	3,852	7/5-11	
		H	708	5.1	11.4	0.1	1.1	-	0.1	4,104	11/8-14	
분진 (51-05-00)	중유회	A	1,056	1.8	59.9	0.2	10.2	0.0	0.1	5,370	12/26	
		B	1,546	27.3	121.0	-	3.1	0.0	0.1	5,232	7/1	