

재활용 폐기물 반입현황 (2017년 상반기)

□ 업체명 : 한라시멘트(옥계공장)

구분	종류		공급자	반입량 (톤) 누계(1~6월)	분석결과								
	대분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (cal/kg)	분석 일자	
대체 원료	유기성오니류 (51-01-00)	폐수오니	A	2,605	-	217.6	35.2	24.1	0.0	-	-	1/4	
			B	1,516	0.1	127.8	3.2	20.0	0.0	-	-	1/4	
			C	1,788	0.9	43.6	-	0.7	0.0	-	-	4/14	
			D	19	0.2	69.9	-	-	0.0	-	-	2/10	
		하수오니	A	5,016	15.7	421.0	1.3	1.2	0.1	-	-	-	1/3
			B	162	13.7	254.9	1.7	1.5	0.0	-	-	-	4/21
			C	97	19.8	331.3	2.0	7.2	0.0	-	-	-	4/21
			D	1,309	5.6	238.4	1.4	10.2	0.0	-	-	-	1/4
			E	243	7.1	80.3	1.2	12.6	0.0	-	-	-	4/13
			F	306	12.4	332.9	0.6	12.9	-	-	-	-	4/21
			G	213	1.2	267.2	0.9	5.5	0.2	-	-	-	5/18
			H	10,419	11.1	434.0	0.8	3.3	-	-	-	-	4/21
			I	3,256	1.3	140.6	0.3	-	-	-	-	-	1/4
			J	231	9.7	9.6	0.2	2.9	-	-	-	-	4/21
			K	19	4.8	13.5	0.1	-	0.0	-	-	-	6/2
			L	3,816	2.5	419.2	0.4	5.6	-	-	-	-	4/21
			M	285	3.7	14.9	0.3	6.1	-	-	-	-	5/18
			N	168	5.0	12.0	0.7	3.3	-	-	-	-	1/4
			O	296	4.8	9.6	0.1	5.7	0.0	-	-	-	6/2
			P	360	7.0	13.6	0.1	-	-	-	-	-	6/2
	Q	169	3.9	13.5	0.5	-	-	-	-	-	6/2		
	R	885	10.0	14.9	0.1	0.1	-	-	-	-	6/2		
	S	110	6.5	11.0	0.1	-	0.0	-	-	-	6/2		
	무기성오니류 (51-02-00)	폐수오니	A	58,820	1.3	11.0	0.2	2.7	0.0	-	-	2/3	
			B	3,659	2.3	11.7	-	-	-	-	-	5/18	
			C	4,585	3.2	112.7	-	1.6	-	-	-	5/18	
		공정오니	A	3,457	0.5	5.6	0.0	-	-	-	-	3/13-19	
			B	1,664	0.7	6.7	-	4.4	-	-	-	1/2-8	
		정수오니	A	805	-	7.6	0.1	1.8	0.0	-	-	2/22	
		무기성오니	A	1,003	0.8	13.4	1.1	11.5	0.0	-	-	5/4	
	폐주물사 및 폐사 (51-06-00)	폐주물사	A	2,623	1.3	62.3	0.1	3.1	0.0	-	-	2/6-12	
			B	20,999	1.2	-	0.1	1.2	0.0	-	-	2/3	
			C	3,651	8.2	64.4	0.3	3.5	0.0	-	-	1/5	
			D	1,355	9.5	129.2	0.2	4.9	-	-	-	3/27	
			E	2,363	47.4	53.3	0.1	8.3	-	-	-	4/1	
			F	1,347	1.2	48.9	0.1	3.2	0.0	-	-	6/19-25	
G			7,758	1.8	85.5	-	0.6	-	-	-	2/6-12		
연소잔재물 (51-13-00)	석탄재	A	807	-	17.3	0.4	35.5	0.0	-	-	6/27		
		B	42,872	1.5	24.8	0.2	10.0	0.1	-	-	1/13		
		C	28,006	2.3	33.4	0.1	19.2	0.0	-	-	1/8		
		D	6,957	5.6	25.2	0.1	15.2	-	-	-	2/18		
		E	4,080	-	15.5	-	-	-	-	-	1/22		
		F	2,123	2.5	18.6	0.1	9.8	0.0	-	-	4/8		
보조 연료	폐합성고분자화합물 (51-03-00)	폐합성수지	A	10	36.8	59.2	0.4	-	0.0	0.5	4,591	4/18-4/24	
			B	7,041	79.4	49.2	0.2	-	-	0.9	5,542	5/2-8	
			C	1,854	18.2	42.3	-	-	-	0.3	6,157	1/24-30	
			D	886	38.6	482.6	0.3	0.3	-	0.4	6,057	1/24-30	
			E	3,499	30.7	54.1	0.2	-	-	0.7	5,080	1/17-23	
			F	7,264	61.3	124.4	1.5	1.4	-	0.8	5,373	5/2-8	
			G	350	99.0	89.5	0.3	1.2	-	1.4	4,517	1/24-30	
			H	875	26.8	313.7	0.4	-	-	0.4	5,863	1/24-30	
			I	2,004	55.6	147.4	1.9	1.0	-	1.3	5,677	3/7-13	
			J	624	14.9	187.2	-	-	-	0.4	6,217	3/7-13	
			K	1,784	26.2	100.5	0.3	2.8	0.1	0.7	5,325	3/7-13	
			L	1,993	42.8	168.8	0.8	-	-	0.5	5,001	5/2-8	
			M	1,038	3.7	75.0	-	-	-	0.3	4,580	3/7-13	
			N	3,855	108.9	78.6	0.9	-	0.0	0.4	5,586	5/2-8	
			O	610	36.1	508.4	-	-	-	0.4	6,193	3/7-13	
			P	55	2.8	51.2	-	-	-	0.1	5,056	1/17-23	
			Q	854	184.0	381.9	0.3	-	-	1.2	5,871	5/2-8	
			R	130	6.8	59.7	0.4	1.8	-	0.1	7,229	1/31-2/6	
			S	2,097	138.5	54.5	1.2	-	-	0.7	5,093	2/14-20	
			T	1,063	92.0	46.7	0.4	2.9	0.0	0.6	4,587	1/10-16	
	U	3,366	34.5	45.1	0.3	2.0	-	0.7	4,540	1/24-26			
	V	1,198	190.5	132.7	0.6	-	-	0.8	4,837	3/7-13			
	W	19,040	34.0	65.7	0.3	-	0.1	0.5	4,662	2/14-20			
	X	145	41.3	45.1	1.6	1.8	-	1.1	4,813	6/13-6/19			
	Y	1,371	11.8	122.4	0.2	-	-	0.1	7,103	1/24-30			
	페타이어 (51-15-00)	페타이어	A	160	8.0	32.5	1.6	1.3	0.0	0.3	4,857	3/21-27	
			B	914	56.6	37.7	0.1	-	-	0.6	4,664	5/2-8	
			C	366	36.1	105.9	0.1	-	-	0.2	5,022	5/2-8	
	폐목재류 (51-20-00)	폐목재류	A	220	9.8	42.3	0.2	0.9	-	0.3	4,088	5/2-8	
			B	1,765	13.9	32.3	0.9	-	-	0.2	3,573	3/7-13	
			C	1,019	19.0	33.2	0.4	-	-	0.3	3,950	1/17-23	
			D	667	24.8	13.9	0.3	1.0	-	0.4	3,830	5/2-8	
			E	895	16.7	8.5	0.0	-	-	0.1	4,598	5/2-8	
			F	17,596	0.6	8.7	0.2	1.3	-	0.3	4,128	3/7-13	
			G	657	28.2	29.9	1.8	1.6	-	0.4	3,594	5/2-8	
			H	2,144	6.4	13.9	1.6	-	-	0.2	4,345	1/17-23	
I			476	0.5	10.6	0.2	-	-	0.2	4,050	5/2-8		
분진 (51-05-00)	중유회	A	280	4.6	39.9	-	12.3	0.0	0.1	5,889	1/3		
		B	1,085	2.6	63.2	-	9.7	0.2	0.1	6,661	1/16		