

재활용 폐기를 반입현황 (2018년 상반기)

□ 업체명 : 한라시멘트(옥계공장)

구분	종류		공급자	반입량 (톤) 누계(1-6월)	분석결과										
	대분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자			
대체 원료	유기성오니류 (51-01)	폐수오니	A	2,674	1.1	102.9	10.8	25.0	-	-	-	-	1/6		
			B	542	1.1	16.0	-	35.4	0.1	-	-	-	5/8		
			C	22	3.5	65.1	11.9	17.8	0.1	-	-	-	3/5		
			A	6,119	12.0	375.3	1.3	4.5	0.0	-	-	-	1/6		
			B	134	3.7	49.6	0.1	9.7	0.1	-	-	-	1/8		
		하수오니	C	119	17.4	70.4	0.1	7.0	0.1	-	-	-	1/4		
			D	22	2.7	65.1	0.2	4.4	0.0	-	-	-	1/4		
			E	474	6.7	414.2	1.6	8.8	0.0	-	-	-	1/6		
			F	413	9.3	288.3	0.8	8.5	-	-	-	-	1/6		
			G	372	13.4	15.9	0.3	8.8	0.1	-	-	-	1/6		
			H	130	2.3	12.0	-	7.8	-	-	-	-	6/27		
			I	1,061	5.0	254.9	10.9	9.7	0.1	-	-	-	6/27		
			J	1,156	2.3	112.8	3.1	12.1	0.0	-	-	-	5/22		
			K	2,499	22.4	124.5	1.9	11.1	0.0	-	-	-	5/22		
			L	814	2.2	78.2	4.1	12.2	0.0	-	-	-	5/22		
			M	1,356	1.3	88.1	2.2	27.4	-	-	-	-	1/6		
			N	1,053	8.0	266.3	0.4	2.2	-	-	-	-	1/5		
			O	8,658	1.0	68.9	-	1.3	0.0	-	-	-	1/4		
			무기성오니류 (51-02)	폐수오니	A	25,303	-	7.3	0.2	0.6	0.0	-	-	-	1/19
					B	1,014	1.6	17.5	0.1	-	0.2	-	-	5/24	
	C	102			0.5	63.5	-	-	0.1	-	-	4/5			
	D	6,569			-	49.1	-	3.7	0.0	-	-	4/9			
	공정오니	A		4,083	3.3	15.6	-	2.5	0.1	-	-	2/6			
		B		24,298	39.4	7.8	0.3	8.5	0.1	-	-	2/21			
		A		699	5.2	8.0	0.1	0.4	-	-	-	4/20			
	정수오니	A	10,227	0.4	12.6	-	-	-	-	-	-	1/15-21			
	폐주물사 및 폐사 (51-06)	폐주물사	A	3,012	1.2	33.2	0.1	-	0.1	-	-	-	5/7-13		
			B	15,401	41.7	533.0	0.8	1.5	0.0	-	-	6/25-6/31			
			C	9,543	1.5	49.0	0.1	8.9	0.0	-	-	1/29-2/4			
			D	6,010	-	78.5	-	8.1	0.1	-	-	6/11-17			
			E	8,948	0.3	64.5	0.2	2.4	0.1	-	-	4/23-29			
	폐석고 (51-12)	폐석고	A	44	1.5	6.7	-	0.1	0.1	-	-	5/25			
	연소잔재물 (51-13)	석탄재	A	2,877	2.5	23.2	0.2	11.5	0.1	-	-	-	6/5		
			B	48,729	3.1	37.2	0.1	5.7	0.1	-	-	5/24			
			C	38,529	2.7	27.4	-	9.5	0.1	-	-	3/15			
			D	6,117	7.2	31.1	-	29.1	0.0	-	-	4/27			
			E	2,093	1.0	16.8	0.1	1.2	0.3	-	-	3/29			
			F	7,030	4.4	21.3	0.1	5.5	0.1	-	-	2/12			
			G	3,525	5.1	30.6	0.2	13.6	0.0	-	-	1/2			
			H	6,094	12.6	36.9	0.1	26.2	0.3	-	-	6/24			
I			2,194	2.1	28.7	0.2	10.1	0.0	-	-	4/18				
보조 원료			폐합성고분자화합물 (51-03)	폐합성수지류	A	20	78.5	199.7	1.1	-	0.0	0.6	4.581	7/3-9	
	B	7			78.2	284.2	-	-	0.0	0.9	5.100	7/2			
	C	5,511			49.4	58.4	3.7	1.2	0.0	0.7	4.600	2/13-19			
	D	1,367			34.7	80.7	0.9	2.7	0.0	0.9	5.482	2/13-19			
	E	1,624			70.6	72.0	0.6	-	0.0	0.6	4.872	3/13-19			
	F	164			137.7	749.8	0.0	-	0.0	0.4	5.426	6/12-18			
	G	3,239			9.2	55.4	0.2	3.1	-	0.9	4.912	1/9-15			
	H	221			13.0	71.5	0.3	-	0.0	0.8	5.121	1/9-15			
	I	8,023			15.2	71.7	0.7	-	0.0	0.4	5.868	4/24-30			
	J	2,222			36.1	66.5	0.8	1.7	0.0	0.9	4.502	2/13-19			
	K	236			0.2	69.0	1.5	0.6	0.0	0.9	6.576	3/13-3/19			
	L	394			45.2	242.3	0.8	0.8	0.0	0.4	5.623	6/19-25			
	M	2,582			38.5	71.5	5.6	3.7	0.0	0.7	6.689	2/20-26			
	N	359			25.6	192.6	3.6	-	0.0	0.9	6.605	6/12-18			
	O	178			182.6	360.3	2.3	-	0.0	0.5	5.541	6/19-6/25			
	P	4,306			41.4	143.4	0.1	-	0.0	0.2	4.579	6/19-25			
	Q	701			87.6	43.4	6.0	-	-	0.7	4.594	2/6-2/12			
	R	2,004			178.9	92.0	1.5	1.3	0.0	0.5	4.524	1/9-15			
	S	362			1.9	3.8	-	-	-	1.4	6.485	1/16-1/22			
	T	166			111.7	71.5	0.3	0.3	0.0	0.6	5.899	2/13-2/19			
	U	9,439	39.0	61.7	1.1	0.6	0.0	0.4	4.797	3/13-19					
	V	274	44.0	601.3	0.2	-	0.1	0.6	5.733	6/19-25					
	W	8,012	23.7	21.4	-	-	-	0.1	4.897	1/8					
	X	860	19.8	164.8	0.1	3.1	0.0	0.5	4.994	2/20-26					
	Y	811	1.5	3.7	-	0.4	0.0	0.1	6.159	4/5					
	Z	3,439	18.4	27.5	0.2	-	0.0	0.4	4.524	6/19-25					
	Z1	47	2.9	86.5	0.9	3.2	0.0	0.9	4.595	1/2-1/8					
	Z2	3,748	37.0	110.7	0.3	-	0.0	1.2	4.865	4/24-30					
	Z3	900	46.0	121.2	2.4	-	0.0	0.6	4.501	3/13-19					
	Z4	15,164	51.2	81.9	0.5	3.6	0.0	0.4	6.853	6/19-25					
	Z5	103	52.4	79.9	1.7	-	-	0.8	5.440	1/23-28					
	Z6	1,904	150.3	169.5	0.5	9.0	0.0	0.5	5.383	4/24-30					
	Z7	446	-	4.2	-	-	0.0	1.2	6.089	4/24-30					
	Z8	912	14.4	285.3	-	2.8	0.0	0.2	7.724	4/24-30					
	페타이어 (51-15)	페타이어	A	7	24.2	79.1	0.5	-	0.0	0.8	8.515	1/29			
	폐목재류 (51-20)	폐목재류	A	806	22.3	13.6	1.5	-	0.1	0.2	3.578	3/13-19			
			B	552	4.1	23.5	-	-	0.1	0.2	3.954	6/19-25			
			C	1,029	8.2	16.8	1.3	-	0.2	0.2	3.943	4/24-30			
			D	832	5.5	6.3	0.2	1.2	-	0.2	4.103	1/9-15			
			E	418	1.6	87.2	-	1.5	0.0	0.5	3.743	3/13-3/19			
F			798	6.0	6.2	-	1.2	0.0	0.3	3.722	6/19-25				
G			14,432	23.8	44.5	0.1	1.5	0.0	0.6	3.594	2/13-19				
H			522	23.8	23.0	-	-	0.0	0.2	3.582	4/24-30				
I			1,936	27.6	34.8	1.5	0.9	0.0	0.4	3.587	5/15-21				
J			717	4.9	10.2	0.6	-	0.0	0.3	3.682	5/22-28				
분진 (51-05)	중유회	A	1,792	1.1	29.3	-	8.3	-	0.0	5.936	1/22-28				