

재활용 폐기물 반입현황 (2018년 하반기)

□ 업체명 : 한라시멘트(옥계공장)

구분	종류		공급자	반입량 (톤) 누계 (7~12월)	분석결과								
	대분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자	
대체 원료	유기성오니류 (51-01)	폐수오니	A	2,430	0.2	32.9	-	16.9	0.1	-	-	7/16	
			A	5,089	-	9.0	0.3	14.7	0.0	-	-	7/16	
			B	141	3.2	46.3	0.7	-	0.0	-	-	10/19	
			C	105	5.6	23.8	0.1	-	0.1	-	-	10/19	
			D	485	2.4	8.0	0.7	6.4	0.0	-	-	7/16	
			E	348	-	12.2	0.1	2.3	0.1	-	-	7/16	
			F	329	36.3	33.9	0.3	23.8	0.0	-	-	10/19	
		하수오니	G	3,286	10.7	20.0	0.5	1.9	0.1	-	-	10/19	
			H	1,643	9.6	18.8	0.9	21.7	0.1	-	-	7/16	
			I	3,687	-	17.8	0.5	6.3	0.1	-	-	7/16	
			J	4,113	0.3	43.8	-	11.2	0.0	-	-	7/16	
			K	2,058	7.5	25.6	0.6	3.3	0.1	-	-	10/19	
			L	1,741	25.6	15.5	0.0	6.8	0.0	-	-	10/19	
			M	813	28.2	316.7	1.4	11.2	-	-	-	10/19	
	무기성오니류 (51-02)	폐수오니	A	26,634	8.5	27.3	0.2	10.3	0.0	-	-	9/18	
			B	1,206	3.2	98.9	0.9	8.5	0.1	-	-	7/12	
			C	82	5.5	123.8	0.9	13.0	0.0	-	-	10/30	
			D	6,885	3.6	112.6	0.2	-	0.0	-	-	9/12	
			E	456	8.0	9.9	0.6	8.8	-	-	-	11/13	
		공정오니	A	2,050	-	18.7	-	5.5	0.1	-	-	8/21	
			B	20,873	2.6	7.7	0.1	-	0.1	-	-	8/29	
			C	475	16.4	15.4	0.6	18.2	0.0	-	-	10/23	
		침수오니	A	1,072	0.3	39.9	-	8.0	0.0	-	-	7/16	
			A	16,583	0.9	12.6	0.1	4.3	0.0	-	-	7/30-8/5	
		폐주물사 및 폐사 (51-06)	폐주물사	A	2,886	13.4	44.1	0.4	0.2	0.0	-	-	12/3-9
				B	12,069	12.2	374.0	0.3	5.0	0.0	-	-	8/13-19
				C	526	30.1	460.7	1.3	5.2	0.0	-	-	12/3
				D	744	10.3	119.7	0.4	7.2	0.1	-	-	12/24
E	10,007			15.4	123.1	0.3	7.5	0.3	-	-	9/24-30		
F	14,379			1.0	79.6	0.2	0.1	0.0	-	-	7/30-8/5		
G	11,838			0.6	126.7	0.2	-	0.1	-	-	7/9-15		
A	22			-	4.0	-	8.0	0.0	-	-	7/24		
연소잔재물 (51-13)	석탄재	A	593	5.7	5.3	0.1	15.6	0.1	-	-	10/22		
		A	1,411	1.1	29.0	0.3	14.2	0.1	-	-	7/18		
		B	283	25.5	157.3	2.0	42.9	0.0	-	-	12/6		
		C	62,497	5.3	37.4	0.2	18.7	0.2	-	-	7/17		
		D	18,176	3.3	26.2	-	20.3	0.2	-	-	9/15		
		E	63,335	17.3	34.0	0.8	21.2	0.0	-	-	10/28		
		F	17,244	12.7	25.1	0.4	17.6	0.3	-	-	10/17		
		G	1,406	14.2	26.7	0.6	25.8	0.2	-	-	12/21		
		H	19,653	14.7	32.4	0.1	17.9	0.3	-	-	7/12		
		I	4,563	-	18.4	-	13.7	0.1	-	-	9/6		
보조 원료	폐합성고분자화합물 (51-03)	폐합성수지류	A	1,698	67.7	105.0	1.4	-	-	0.4	4,715	10/16-22	
			B	505	23.1	33.9	3.7	8.5	-	0.8	5,484	7/18	
			C	10,473	18.6	-	0.2	0.6	0.0	0.7	5,110	7/17-23	
			D	1,525	41.2	64.3	1.7	6.7	-	0.2	4,543	7/17-23	
			E	55	20.4	41.0	0.7	10.3	0.3	0.2	5,829	7/10-7/16	
			F	4,064	12.1	45.1	0.3	-	0.2	1.0	4,558	8/14-20	
			G	9,458	127.3	122.3	8.5	2.8	-	0.6	5,876	12/11-17	
			H	2,689	46.1	121.2	0.5	-	0.0	0.6	4,549	7/17-23	
			I	3,683	35.5	93.9	-	-	0.0	0.4	5,561	7/17-23	
			J	4,139	100.5	247.3	0.9	-	0.0	0.4	4,577	7/17-23	
			K	1,975	9.1	39.4	1.0	3.2	0.0	0.7	4,650	10/30-11/5	
			L	35	61.7	160.3	0.1	8.9	0.0	0.3	5,731	7/17-7/23	
			M	6,836	22.8	-	0.6	4.1	0.0	0.4	4,992	7/17-23	
			N	2,925	13.8	20.6	-	-	0.0	0.8	4,817	7/17-23	
			O	284	1.6	3.1	-	12.2	0.2	1.4	5,886	7/24-7/30	
			P	16,667	43.9	94.2	0.6	-	0.1	0.5	4,550	7/17-23	
			Q	776	24.1	199.8	0.3	1.8	0.1	0.4	5,521	7/24-7/30	
			R	13	17.2	8.4	-	4.1	-	0.2	4,600	11/1	
			S	5,173	64.7	59.4	6.4	-	0.0	0.5	4,556	12/11-17	
			T	4,224	43.2	57.1	0.2	1.7	0.0	0.2	5,145	9/4-10	
	U	172	56.8	247.9	1.0	2.3	0.0	0.4	5,548	7/17-23			
	V	10,830	63.0	69.8	0.5	5.2	0.0	0.5	6,477	7/17-23			
	W	123	1.6	3.9	0.1	8.5	0.0	1.1	5,781	8/21-8/27			
	X	1,852	23.6	72.6	0.1	-	0.0	0.8	4,899	7/17-23			
	Y	453	-	1.8	-	-	-	0.9	5,784	10/16-22			
	Z	795	15.5	118.8	0.1	5.8	0.1	0.1	6,548	7/24-30			
	폐목재류 (51-20)	폐목재류	A	666	23.6	31.7	0.7	0.9	-	0.1	3,564	12/11-17	
			B	2,366	8.4	9.6	0.7	-	0.0	0.1	3,588	9/4-10	
			C	1,413	18.3	89.8	1.0	-	0.0	0.2	3,561	9/4-10	
			D	1,249	21.0	11.4	1.8	1.1	0.1	0.1	3,652	8/14-20	
E			818	21.2	5.9	0.3	-	-	0.3	3,944	10/16-22		
F			16,887	-	11.5	-	0.9	-	0.2	4,331	7/17-23		
G			26	22.0	178.6	0.5	-	-	0.2	3,531	7/10-7/16		
H			1,429	26.4	27.4	1.6	1.3	0.0	0.3	3,550	7/24-30		
본진 (51-05)	중유회	A	569	37.3	94.5	-	10.6	0.0	0.0	5,753	8/29		