

재활용 폐기물 반입현황 (2019년 상반기)

□ 업체명 : 한라시멘트(옥계공장)

구분	종류		공급자	반입량 (톤) 누계(1~6월)	분석결과								
	대분류	세분류			Pb	Cu	Cd	As	Hg	Cl	저위발열량	분석일자	
					(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(%)	(kal/kg)		
대체 원료	유기성오니류 (51-01)	폐수오니	A	3,444	5.9	102.1	0.6	4.4	0.0	-	-	5/9	
			B	847	9.9	102.9	0.9	5.1	0.3	-	-	5/9	
			C	445	18.7	179.7	1.2	1.7	0.0	-	-	1/24	
			D	133	23.3	146.2	0.6	0.9	0.1	-	-	5/9	
		하수오니	A	7,157	20.6	392.6	1.9	6.1	0.1	-	-	1/24	
			B	145	12.2	192.8	0.5	20.2	0.2	-	-	1/22	
			C	135	9.3	132.2	0.5	7.2	0.1	-	-	1/22	
			D	552	7.8	203.5	1.7	-	0.1	-	-	1/23	
			E	431	19.1	448.9	1.5	9.6	0.0	-	-	1/23	
			F	435	4.7	353.3	11.8	14.0	0.1	-	-	1/23	
			G	364	8.3	262.3	1.3	6.6	0.1	-	-	1/22	
			H	3,965	9.7	130.7	0.9	7.7	0.1	-	-	1/23	
			I	2,439	9.3	104.5	0.8	10.2	0.2	-	-	1/22	
			J	515	13.7	353.3	1.4	3.4	0.0	-	-	5/22	
			K	140	5.6	257.3	1.0	3.0	0.2	-	-	5/15	
			L	4,142	10.9	117.2	0.9	10.3	0.0	-	-	1/26	
			M	1,727	10.0	195.7	0.7	8.4	0.3	-	-	1/21	
			N	324	5.9	101.0	1.0	6.2	0.0	-	-	1/23	
			O	1,775	14.7	239.7	1.6	13.4	0.0	-	-	1/24	
			P	1,635	3.4	46.4	2.4	25.8	0.0	-	-	1/23	
	Q	1,026	26.8	186.0	0.7	7.1	0.2	-	-	5/22			
	R	176	11.1	92.7	0.8	10.1	0.2	-	-	4/18			
	무기성오니류 (51-02)	폐수오니	A	25,655	13.7	13.1	1.1	8.5	0.2	-	-	3/20	
			B	973	11.6	6.8	0.6	13.7	0.1	-	-	5/9	
			C	104	17.8	425.7	2.2	6.6	0.1	-	-	5/19	
			D	5,754	15.3	81.9	1.0	1.4	0.1	-	-	3/19	
			E	538	6.6	7.5	0.7	12.7	0.1	-	-	5/31	
			F	1,170	1.0	24.7	0.6	5.5	0.1	-	-	5/14	
			G	50	12.0	39.4	1.3	4.1	0.2	-	-	5/21	
			H	909	12.9	38.8	7.1	9.9	0.2	-	-	1/27	
			I	1,611	14.5	76.8	5.8	3.4	0.1	-	-	2/23	
			J	719	11.5	178.9	0.6	12.9	0.1	-	-	5/1	
		공정오니	A	1,514	18.5	15.0	0.6	23.3	0.1	-	-	4/16	
			B	13,922	17.3	9.0	0.8	7.4	0.1	-	-	4/1~7	
			C	4,280	65.5	21.9	0.7	26.0	0.1	-	-	4/1~7	
			정수오니	A	961	13.9	265.3	0.5	2.1	0.1	-	-	4/15
	그밖의오니	A	19,690	10.4	18.8	0.8	6.0	0.1	-	-	2/25~3/3		
	폐주물사 및 폐사 (51-06)	폐주물사	A	2,993.4	14.7	27.6	0.4	7.2	0.1	-	-	3/11~17	
			B	5,128.6	9.9	18.9	0.7	10.5	0.1	-	-	6/4	
			C	506.7	36.4	325.0	1.4	2.4	0.1	-	-	2/19	
			D	1,897.4	25.8	284.1	0.7	-	0.2	-	-	2/18	
			E	3,890	15.4	110.0	0.7	15.9	0.1	-	-	3/11~17	
			F	8,441	6.1	67.9	0.4	6.2	0.0	-	-	1/28~2/3	
			G	10,289	8.7	62.4	0.4	5.8	0.0	-	-	5/13~19	
	폐석회 (51-12)	폐석회	A	2,292	7.0	15.1	0.4	11.9	0.0	-	-	4/15~21	
	연소잔재물 (51-13)	석탄재	A	2,172	24.0	156.1	1.7	27.1	0.1	-	-	1/23	
			B	37,391	15.8	44.2	0.9	20.7	0.3	-	-	6/25	
			C	10,472	14.3	31.1	0.4	16.0	0.0	-	-	4/8	
			D	31,760	10.2	37.0	0.3	20.1	0.1	-	-	3/30	
			E	10,945	14.5	31.3	0.3	31.2	0.2	-	-	3/2	
			F	18,260	11.6	25.0	1.6	12.8	0.4	-	-	4/14	
			G	2,867	18.7	32.2	0.5	30.3	0.2	-	-	1/11	
			H	3,041	11.8	43.1	0.6	13.3	0.1	-	-	2/7	
			I	6,018	13.8	24.1	0.5	22.2	0.3	-	-	6/29	
	보조 원료	폐합성고분자화합물 (51-03)	폐합성수지류	A	2,037	66.4	63.4	1.6	4.9	0.1	1.2	5,354	4/30~5/6
				B	423	93.3	172.5	0.8	6.7	0.1	0.5	4,847	5/7~5/13
				C	13,014	38.1	100.6	1.3	7.6	0.1	0.5	4,528	6/18~24
				D	3,548	113.6	53.5	4.3	4.9	0.0	0.5	5,035	4/2~8
				E	4,128	36.4	67.8	1.6	2.1	0.0	0.6	4,878	4/30~5/6
				F	7,829	44.3	150.7	5.7	-	0.0	0.6	5,220	4/30~5/6
				G	5,093	135.0	102.1	1.0	7.0	-	0.4	4,522	1/1~7
				H	5,353	128.5	371.4	3.4	4.6	0.1	0.6	4,528	4/30~5/6
				I	3,569	22.1	1.6	1.9	1.7	0.0	0.6	4,559	6/18~24
				J	485	64.8	205.6	3.5	5.8	0.0	0.3	5,785	1/15~1/21
				K	6,460	15.9	41.9	0.4	4.5	0.0	0.1	5,628	6/18~24
				L	2,457	101.8	159.9	1.5	-	0.4	0.8	4,876	6/18~24
				M	393	-	2.9	0.1	-	0.2	1.5	6,129	6/18~24
				N	12,355	-	7.0	0.2	-	0.0	0.5	4,711	4/2~8
				O	492	51.8	219.2	0.5	2.9	0.1	0.5	5,850	6/18~24
				P	21	-	1.7	-	-	0.0	0.8	5,567	5/14~5/20
				Q	4,407	128.7	51.0	2.4	10.0	0.0	0.4	4,506	4/2~8
				R	3,053	36.8	51.4	3.0	0.1	0.0	1.3	4,513	6/18~24
				S	6,056	163.0	91.3	1.2	2.1	0.0	0.2	6,400	4/2~8
				T	247	-	2.6	-	5.4	0.3	1.1	5,944	6/18~24
	U	1,293	29.2	55.7	-	3.3	0.0	0.6	4,594	6/11~6/17			
	V	472	4.5	-	0.3	-	0.1	1.1	5,917	4/23~29			
	W	624	17.6	44.9	0.4	1.3	-	1.2	6,138	5/28~6/3			
	폐목재류 (51-20)	폐목재류	A	534	11.0	12.8	1.7	0.5	0.1	0.2	3,548	6/18~24	
			B	1,815	25.6	154.9	0.2	1.1	0.1	0.4	3,580	1/1~7	
			C	1,147	12.5	10.5	0.6	0.3	0.1	0.1	3,940	1/1~7	
			D	1,030	11.6	44.9	0.6	0.5	0.0	0.2	3,955	4/2~8	
			E	743	7.5	17.0	0.8	-	0.1	0.3	3,903	6/18~24	
			F	13,090	6.7	8.9	1.2	1.4	0.0	0.2	4,064	4/30~5/6	
			G	98	17.6	44.9	1.2	1.8	0.1	0.4	4,193	1/22~1/28	
			H	260	3.8	15.4	0.9	1.6	0.1	0.2	4,559	2/26~3/4	
	분진 (51-05)	중유회	A	94	30.0	12.5	0.6	1.3	0.0	5,583	2/11		