

재활용 폐기물 반입현황 (2012년 상반기)

□ 업체명 : 라파즈한라시멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계(1~6월)	분석결과							
	대분류	중분류	세분류			Pb	Cu	Cd	As	Hg	Cl	저위발열량 (kcal/kg)	분석일자
						(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(mg/kg)	(%)		
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수처리오니	A	1,101	19.2	402.2	1.2	3.6	-	0.1	-	3/19
				B	21	6.0	211.2	9.9	42.1	0.0	0.2	-	6/11
		하수처리오니 (51-01-04)	하수처리오니	A	1,542	56.1	263.0	2.5	13.2	0.0	0.0	-	5/4
				B	2,296	27.0	497.9	2.1	8.4	0.7	0.0	-	5/5
				C	7	27.0	497.9	2.1	8.4	0.7	0.0	-	5/5
				D	7	27.0	497.9	2.1	8.4	0.7	0.0	-	5/5
				E	345	30.7	380.0	1.6	7.7	0.1	0.1	-	3/19
				F	536	36.8	618.7	4.3	18.3	0.0	0.0	-	5/5
				G	306	20.6	279.4	1.4	2.7	0.0	0.5	-	5/9
				H	813	25.3	577.8	5.6	20.3	1.1	0.0	-	5/6
				I	485	24.5	721.0	1.6	3.3	0.0	0.1	-	5/9
				G	311	20.6	279.4	1.4	2.7	0.0	0.5	-	5/9
				K	249	33.6	447.9	6.6	11.9	0.1	0.1	-	5/6
				L	4,003	34.3	417.6	1.4	5.2	0.1	0.1	-	5/6
				M	2,070	36.0	366.3	1.6	0.1	0.2	0.1	-	5/12
				N	714	47.9	328.6	2.1	8.6	0.0	0.0	-	5/6
				O	1,084	29.9	379.7	1.6	5.0	0.0	0.1	-	6/8
	무기성오니류 (51-02-00)	무기성오니류 (51-02-02)	공정오니	A	285	10.0	26.1	0.3	7.2	0.2	0.0	-	6/8
				B	124	9.4	35.0	0.3	12.8	0.1	0.0	-	6/8
		정수처리오니 (51-02-03)	정수처리오니	A	470	36.8	497.9	2.1	8.4	0.7	0.0	-	5/5
	연소잔재물 (51-13-00)		석탄재	A	28,119	20.8	32.7	0.5	19.5	0.5	0.0	-	6/20
				B	42,259	139.0	402.2	0.9	13.9	0.1	0.0	-	6/22
				C	1,531	5.6	25.6	0.2	21.7	0.1	0.0	-	1/26
				D	17,729	14.6	29.8	0.1	11.5	0.0	0.0	-	6/17
				E	1,000	11.6	32.6	0.1	14.0	0.0	0.0	-	6/27
	폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	2,294	2.0	14.2	0.1	2.9	0.3	0.0	-	1/3
B				12,035	27.6	337.5	0.7	5.2	0.1	0.0	-	6/20	
C				4,941	9.6	48.0	0.2	5.0	0.0	0.0	-	6/23	
광재류 (51-04-00)	제강슬래그 (51-04-02)	제강슬래그	A	1,406	7.4	11.7	1.7	0.0	0.0	0.0	-	6/10	
			B	171	10.2	22.6	2.2	0.0	0.0	-	6/24		
	기타 광재류 (51-04-03)	기타 광재류	A	20,186	2.2	15.0	1.4	1.6	0.0	0.0	-	6/24	
			B	1,144	72.1	147.9	0.0	8.7	0.0	0.0	-	6/20	
폐석고 및 폐석회 (51-12-00)	폐석고 (51-12-01)	폐석고	A	1,050	34.7	38.4	2.6	0.4	0.1	0.0	-	6/1	
폐보드류 (51-32-00)		폐보드류	A	423	7.6	14.7	0.3	5.9	0.2	0.0	-	6/1	
그 밖의 폐기물 (51-99-00)		혼합철	A	15,845	109.8	44.8	5.5	8.9	0.7	0.0	-	6/17	
대체 원료	폐합성 고분자 혼합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	523	178.0	556.0	2.3	1.0	0.0	0.3	5,215	1/3
				B	6,992	113.2	268.7	0.9	2.0	0.6	1.1	5,152	5/29
				C	7,250	182.0	282.6	3.2	2.1	0.1	0.5	4,544	6/19
				D	356	27.3	55.5	0.3	0.0	0.0	0.6	4,545	6/26
				E	1,648	164.5	78.8	0.9	0.6	0.0	1.7	4,911	3/20
				F	2,797	135.8	165.3	6.3	2.8	0.0	1.5	6,389	6/19
				G	2,652	144.8	357.2	4.9	3.1	0.0	1.8	5,356	5/22
				H	9,273	129.2	115.8	1.8	3.4	0.0	0.5	4,905	6/26
				I	3,467	51.1	221.9	0.5	6.2	0.1	0.6	4,778	6/26
				J	2,803	34.9	82.3	0.7	2.3	0.0	0.8	4,803	5/29
				K	8,436	187.2	300.5	1.3	0.0	0.0	0.8	5,185	6/5
				L	5,992	138.7	266.1	1.7	2.8	0.1	1.3	5,351	6/26
				M	4,483	51.1	221.9	0.5	6.2	0.1	1.7	5,167	6/12
				N	1,811	45.3	200.2	3.4	0.0	0.0	0.9	4,962	2/14
				O	232	189.4	41.0	1.0	0.6	0.0	0.6	4,555	3/20
				P	1,068	84.7	302.3	0.6	0.8	0.1	1.0	4,547	4/24
				Q	376	197.2	50.9	0.7	0.9	0.0	0.3	4,532	1/10
				R	296	45.6	58.8	3.1	8.8	0.0	0.9	6,045	5/22
				S	489	88.2	426.5	0.5	1.0	0.0	0.4	4,614	5/15
				T	1,590	66.4	74.0	0.9	3.2	0.0	1.3	6,787	6/19
	U	235	27.0	125.2	0.4	1.6	0.0	0.2	4,581	4/3			
	V	20	107.6	121.3	3.1	0.0	0.0	0.9	5,012	4/18			
	W	27	105.2	78.2	4.4	0.0	0.0	1.1	5,948	3/19			
		폐합성고무류 (51-03-02)	폐고무	A	351	21.9	42.3	0.2	0.0	0.0	0.4	5,674	6/5
				B	125	24.3	576.0	2.5	0.0	0.0	0.1	5,021	5/1
	페타이어 (51-15-00)		페타이어	A	89	34.8	54.9	1.9	0.0	0.0	0.2	6,923	1/12
				B	2,264	47.1	302.2	1.4	0.0	0.0	0.3	6,619	6/19
C				108	27.0	125.2	0.4	1.6	0.0	0.2	4,581	4/3	
페목재류 (51-20-00)		페목재류	A	198	14.1	19.0	1.2	0.0	0.0	0.4	3,645	6/5	
			B	1,044	22.2	13.6	0.2	1.4	0.0	0.2	4,004	5/22	