

재활용 폐기물 반입현황 (2013년 상반기)

□ 업체명 : 라파즈한라시멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계(1~6월)	분석결과										
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석일자			
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수처리오니	A	312	6.0	211.2	9.9	42.1	0.0	-	-	3/20			
				B	461	9.6	172.9	2.5	21.0	0.1	-	-	3/11			
				C	311	0.3	12.5	0.0	0.0	0.0	-	-	3/20			
		하수처리오니 (51-01-04)	하수처리오니	A	3,101	30.0	563.3	2.7	8.2	0.2	-	-	3/4			
				B	70	22.1	154.8	1.6	11.2	0.0	-	-	3/13			
				C	62	14.0	513.8	1.6	8.1	-	-	-	3/5			
				D	1,158	21.8	399.6	3.1	6.8	0.0	-	-	3/8			
				E	357	12.9	235.1	0.9	4.0	0.0	-	-	3/4			
				F	342	23.9	710.1	2.4	4.4	0.0	-	-	3/21			
				G	10,847	15.1	511.1	0.8	6.8	0.0	-	-	3/11			
				H	1,944	14.1	490.6	1.5	7.3	0.2	-	-	3/11			
				I	947	19.3	203.1	1.1	2.8	0.1	-	-	3/11			
				J	1,747	32.3	382.7	2.3	10.3	0.0	-	-	3/4			
				K	740	29.8	280.2	1.6	9.0	0.0	-	-	3/4			
				L	387	28.7	408.1	6.2	12.0	0.6	-	-	3/8			
				M	507	35.0	583.4	5.9	26.8	-	-	-	3/9			
				N	721	14.6	704.5	1.1	7.9	0.0	-	-	3/11			
				O	1,156	31.4	372.5	1.4	2.9	0.4	-	-	6/27			
				P	75	96.6	781.8	4.7	13.0	1.4	-	-	3/14			
	무기성오니류 (51-02-00)	무기성오니류 (51-02-02) 정수처리오니 (51-02-03)	공정오니 정수처리오니	A	224	10.0	26.1	0.3	7.2	0.2	-	-	3/20			
A				502	28.5	561.8	2.8	7.0	0.1	-	-	3/5				
연소잔재물 (51-13-00)		석탄재	A	20,714	18.1	28.7	0.3	18.2	0.3	-	-	6/10				
			B	34,428	10.7	69.7	0.3	13.0	0.1	-	-	6/12				
			C	9,527	9.2	63.3	-	8.4	0.0	-	-	5/26				
광재류 (51-04-00)	제강슬래그 (51-04-02) 기타 광재류 (51-04-03)	제강슬래그 기타 광재류	A	18,776	12.0	22.9	-	6.6	-	-	-	6/23				
			A	15,634	9.0	15.2	1.9	3.0	-	-	-	6/23				
폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	9,906	14.4	64.4	0.2	4.9	-	-	-	6/27				
			B	1,103	2.2	71.2	0.7	2.0	-	-	-	5/21				
			C	34,185	16.4	164.8	0.9	6.5	0.0	-	-	6/28				
폐보드류 (51-32-00)		폐보드류	A	622	7.6	14.7	0.3	5.9	0.2	-	-	3/3				
그 밖의 폐기물 (51-99-00)		혼합질	A	3,591	136.7	135.2	6.8	9.7	0.4	-	-	3/3				
대체 연료	폐합성 고분자 화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	165	107.2	32.5	2.0	4.5	0.0	0.6	4,516	5/27			
				B	856	127.9	85.6	1.1	0.0	0.1	1.7	4,866	3/26			
				C	2,689	49.0	160.2	1.2	0.0	0.0	0.5	6,443	5/21			
				D	2,206	103.6	80.4	0.5	4.5	0.1	0.6	4,926	4/9			
				E	3,860	60.9	124.6	2.5	0.0	0.0	1.5	4,616	5/14			
				F	783	185.8	70.2	2.0	1.8	0.0	1.3	4,636	5/14			
				G	160	102.8	97.4	5.1	5.8	0.0	0.2	4,585	5/27			
				H	2,842	12.8	41.5	0.0	0.0	0.1	0.8	4,929	3/26			
				I	13,201	80.5	126.1	2.9	1.5	0.8	0.9	4,877	6/24			
				J	7,373	87.5	73.6	2.0	1.0	-	1.0	4,997	5/14			
				K	686	47.7	104.6	0.3	0.0	0.0	0.8	4,555	3/5			
				L	7,474	104.0	449.7	1.2	-	0.0	0.9	4,588	5/14			
				M	11,290	172.4	87.1	0.9	-	0.3	0.8	4,928	5/28			
				N	3,982	174.6	792.2	4.0	1.9	0.2	1.2	4,601	1/29			
				A	1,134	47.9	147.6	0.5	-	-	1.6	5,087	6/17			
				B	1,368	119.7	31.7	2.9	2.2	0.0	0.4	5,803	2/26			
				페타이어 (51-15-00)		페타이어	A	2,280	18.3	271.6	0.7	-	-	0.3	6,146	6/17
				폐목재류 (51-20-00)		폐목재류	A	348	8.8	11.3	0.1	0.4	-	0.7	3,697	6/10
	분진 (51-05-00)		중유회	A	575	4.0	323.3	0.2	3.7	0.1	0.0	6,300	3/22			