

**재활용 폐기를 반입현황 (2014년 상반기)**

□ 업체명 : 라파즈하라스멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계 (1~6월)	분석결과							
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수처리오니	A	344	21.2	218.4	2.4	2.9	1.4	-	-	6/23
				A	3,247	34.9	204.0	1.0	2.1	0.1	-	-	5/7
				B	97	56.3	349.0	0.8	4.3	0.1	-	-	5/4
				C	70	78.4	321.0	2.0	5.5	1.3	-	-	5/15
				D	1,327	56.2	129.0	2.3	6.7	0.0	-	-	5/3
				E	80	79.9	322.5	3.5	7.0	0.9	-	-	5/5
		F	268	38.9	629.2	0.1	3.2	0.9	-	-	6/26		
		G	272	46.3	284.0	0.9	7.8	0.0	-	-	5/3		
		하수처리오니 (51-01-04)	하수처리오니	H	11,232	16.4	341.0	1.0	5.6	0.0	-	-	4/4
				I	2,963	15.8	341.5	1.0	1.6	0.0	-	-	4/4
				J	1,565	12.4	458.8	1.5	3.3	0.2	-	-	4/5
				K	1,175	16.0	661.3	0.8	6.0	0.0	-	-	4/7
				L	1,039	42.9	297.0	1.1	4.7	0.0	-	-	5/5
				M	355	34.1	18.8	-	1.3	-	-	-	2/20
	N			1,190	57.4	350.1	1.9	5.4	1.2	-	-	5/11	
	O			330	42.7	553.4	11.2	8.7	1.3	-	-	4/26	
	무기성오니류 (51-02-00)	무기성오니 (51-02-00)	무기성오니	A	339	1.8	12.0	0.1	-	0.0	-	-	5/27
				B	33,649	20.8	12.7	0.7	8.7	0.0	-	-	5/20
		폐수처리오니 (51-02-01)	폐수처리오니	C	606	13.1	7.7	-	6.9	0.0	-	-	6/13
				D	2,105	2.4	5.5	0.2	1.0	-	-	-	5/28
	공정오니 (51-02-02)	공정오니	E	822	111.4	128.2	1.5	1.9	1.7	-	-	6/26	
			F	822	111.4	128.2	1.5	1.9	1.7	-	-	6/26	
	정수처리오니 (51-02-03)	정수처리오니	G	822	111.4	128.2	1.5	1.9	1.7	-	-	6/26	
			H	822	111.4	128.2	1.5	1.9	1.7	-	-	6/26	
			I	822	111.4	128.2	1.5	1.9	1.7	-	-	6/26	
	연소잔재물 (51-13-00)		석탄재	A	19,760	4.6	27.6	0.2	10.4	0.2	-	-	6/13
				B	48,171	11.8	53.0	0.3	13.2	0.2	-	-	2/15
				C	34,545	13.0	30.1	0.1	16.9	0.3	-	-	2/18
	광재류 (51-04-00)	제강슬래그 (51-04-02)	제강슬래그	A	24,327	56.9	7.3	-	3.7	-	-	-	6/24
				B	737	-	12.6	-	-	-	-	-	5/14
기타 광재류 (51-04-03)		기타 광재류	C	1,388	6.0	14.0	5.6	-	-	-	-	5/29	
폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	2,497	12.1	52.3	0.5	8.8	-	-	-	5/14	
			B	16,466	18.8	34.7	0.1	3.5	0.0	-	-	4/29	
			C	1,140	-	11.8	-	1.7	-	-	-	6/13	
			D	1,189	9.0	96.3	1.2	4.4	-	-	-	5/20	
			E	2,036	7.0	61.2	0.4	3.6	-	-	-	5/27	
			F	32,078	13.6	123.6	0.8	5.8	0.0	-	-	5/24	
폐석고 및 폐석회 (51-12-00)	폐석고 (51-12-01)	폐석고	A	1,419	10.3	123.1	6.3	4.7	1.7	-	-	3/25	
페보드류 (51-32-00)	페보드	A	721	6.9	14.7	0.1	-	0.0	-	-	6/19		
그 밖의 폐기물 (51-99-00)		혼합철	A	2,638	117.1	36.6	9.8	11.6	0.8	-	-	6/11	
보조 원료	폐합성고분자화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	24	21.0	102.0	1.2	2.8	0.0	0.4	4,558	4/2
				B	9,955	30.0	40.2	0.8	-	0.0	0.7	5,189	4/2
				C	1,137	98.9	260.1	1.0	-	0.2	0.6	4,802	4/9
				D	27	175.2	145.2	8.6	1.9	-	1.9	4,543	3/26
				E	9,864	45.0	101.0	0.3	-	0.1	0.7	4,815	5/7
				F	5,656	159.1	257.8	3.3	3.3	0.1	1.6	6,332	4/9
				G	6,535	69.4	109.9	0.4	-	0.1	0.7	5,065	4/2
				H	2,893	24.5	25.9	2.6	3.9	0.0	0.9	4,507	4/2
				I	314	28.7	101.9	0.4	1.6	-	0.3	6,236	3/12
				J	2,410	78.2	45.6	0.3	0.7	-	0.5	6,502	3/12
				K	1,763	45.8	64.9	0.2	-	0.1	0.2	4,649	5/28
				L	7,085	52.5	74.2	0.4	6.9	0.1	0.6	4,588	4/30
				M	62	43.9	181.0	0.7	2.1	0.3	0.4	5,581	3/12
				N	1,408	71.0	128.4	1.7	0.6	0.0	0.8	5,789	2/5
	O	170	15.8	185.4	0.1	1.1	-	0.1	4,925	6/11			
	폐합성고무류 (51-03-02)	폐고무	A	622	33.5	549.4	6.7	6.8	-	0.2	4,598	4/30	
			B	3,555	23.7	55.5	0.3	9.8	0.0	0.1	5,708	4/30	
			C	348	44.1	678.9	4.2	6.1	-	0.1	5,460	4/30	
	페목재류 (51-20-00)		페목재	A	317	9.8	6.5	0.6	-	0.0	0.3	3,929	5/28
				B	610	24.3	9.0	0.2	-	0.1	0.3	4,119	5/28
	분진 (51-05-00)		중유회	A	136	41.3	498.4	2.5	6.1	0.2	0.4	4,579	1/28
				B	802	32.7	207.2	-	11.4	-	0.2	5,422	3/18
				C	1,496	4.9	35.6	-	1.8	0.0	0.3	7,115	3/18