

재활용 폐기물 반입현황 (2012년 하반기)

□ 업체명 : 라파즈한라시멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계(7-12월)	분석결과									
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자		
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수처리오니	A	209	6.0	211.2	9.9	42.1	0.0	-	-	9/21		
				B	97	11.7	246.6	5.5	33.0	0.1	-	-	11/6		
				C	427	0.3	12.5	0.0	0.0	0.0	-	-	12/20		
		하수처리오니 (51-01-04)	하수처리오니	A	2,165	32.0	593.0	2.7	4.6	0.4	-	-	10/2		
				B	558	32.0	593.0	2.7	4.6	0.4	-	-	10/2		
				C	19	32.0	593.0	2.7	4.6	0.4	-	-	10/2		
				D	463	36.8	618.7	4.3	18.3	0.0	-	-	9/20		
				E	295	31.0	694.5	1.6	4.8	0.0	-	-	9/21		
				F	279	23.9	710.1	2.4	4.4	0.0	-	-	9/21		
				G	1,491	19.9	403.9	1.6	5.4	0.0	-	-	12/3		
				H	24	19.9	403.9	1.6	5.4	0.0	-	-	12/3		
				I	47	19.9	403.9	1.6	5.4	0.0	-	-	12/3		
				J	1,229	66.7	380.3	3.5	10.3	0.0	-	-	9/21		
				K	781	53.8	355.9	2.1	7.3	1.8	-	-	9/21		
				L	274	33.6	447.9	6.6	11.9	0.1	-	-	9/21		
				M	380	25.3	577.8	5.6	20.3	1.1	-	-	9/20		
				N	738	31.0	694.5	1.6	4.8	0.0	-	-	9/21		
				O	329	30.7	380.0	1.6	7.7	0.1	-	-	9/20		
				P	925	34.3	417.6	1.4	5.2	0.1	-	-	9/20		
	Q	1,445	36.0	366.3	1.6	0.1	0.2	-	-	9/21					
	무기성오니류 (51-02-00)	무기성오니류 (51-02-02)	공정오니	A	270	9.4	35.0	0.3	12.8	0.1	-	-	9/20		
				B	409	10.0	26.1	0.3	7.2	0.2	-	-	9/20		
	정수처리오니 (51-02-03)	정수처리오니	A	580	36.2	552.1	2.5	5.8	0.2	-	-	9/21			
	연소잔재물 (51-13-00)		석탄재	A	21,957	21.8	34.5	0.7	18.1	0.6	-	-	11/17		
				B	27,844	5.2	34.9	0.8	33.4	1.0	-	-	11/29		
				C	12,096	11.3	35.3	0.4	22.4	0.0	-	-	8/26		
	광재류 (51-04-00)	제강슬래그 (51-04-02)	제강슬래그	A	10,747	12.4	11.9	0.0	6.2	0.1	-	-	12/27		
B				266	3.7	15.8	1.5	2.2	0.0	-	-	7/15			
기타 광재류 (51-04-03)	기타 광재류	A	14,879	13.5	31.0	4.1	4.0	0.0	-	-	12/30				
폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	484	41.5	132.8	1.0	4.0	0.3	-	-	9/22			
			B	1,521	24.4	104.2	0.8	3.3	0.2	-	-	10/12			
			C	7,580	19.5	105.8	0.8	2.3	0.1	-	-	7/19			
폐보드류 (51-32-00)		폐보드류	A	348	7.6	14.7	0.3	5.9	0.2	-	-	7/3			
그 밖의 폐기물 (51-99-00)		혼합철	A	11,681	120.5	35.2	4.8	7.0	0.5	-	-	12/30			
대체 원료	폐합성 고분자 화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	27	26.5	19.3	0.3	6.0	0.0	0.6	4,789	8/21		
				B	445	85.8	261.6	0.8	0.0	0.5	0.6	4,636	10/25		
				C	2,822	80.8	121.9	8.1	1.6	0.0	0.6	5,783	12/31		
				D	2,271	86.2	65.0	0.5	4.4	0.1	0.4	6,091	12/31		
				E	4,535	88.4	60.7	0.7	0.0	0.3	1.4	4,761	12/25		
				F	204	27.0	125.2	0.4	1.6	0.0	0.2	4,515	7/17		
				G	2,475	59.3	97.6	0.3	5.2	0.2	0.8	5,581	12/31		
				H	8,851	98.7	309.4	0.8	3.1	0.1	0.9	5,672	12/31		
				I	1,374	71.7	105.6	1.0	0.0	0.1	0.9	4,743	11/6		
				J	9,789	91.3	145.7	3.2	2.2	0.7	1.2	4,534	12/31		
				K	1,134	4.5	12.6	0.3	2.0	0.0	0.6	5,328	12/31		
				L	1,439	187.1	133.8	5.8	2.2	0.1	0.6	4,529	12/31		
				M	26	141.1	701.4	7.9	10.2	0.0	0.6	4,548	8/14		
				N	1,666	65.4	218.8	3.9	0.8	0.0	1.1	4,530	8/14		
				O	11,744	85.2	136.6	3.0	0.0	0.1	1.1	5,935	12/31		
				P	6,886	191.4	203.0	8.0	7.2	0.3	1.4	4,829	12/31		
				Q	104	100.2	600.4	0.3	11.3	0.0	0.7	4,996	8/14		
				폐합성고무류 (51-03-02)	폐고무	A	111	21.9	42.3	0.2	0.0	0.0	0.4	5,674	8/28
						B	557	27.5	320.8	1.6	2.7	0.0	0.3	7,018	7/17
				페타이어 (51-15-00)		페타이어	A	303	21.8	97.8	0.5	0.0	0.3	0.1	6,440
	B	3,634	30.0				361.1	3.0	2.2	0.0	0.3	5,265	12/11		
	폐목재류 (51-20-00)		폐목재류	A	720	19.9	22.8	0.5	1.0	0.0	0.4	3,761	12/4		
	분진 (51-05-00)		중유회	A	56	4.9	30.9	0.1	9.2	1.0	0.0	7,082	10/2		