

재활용 폐기물 반입현황 (2013년 하반기)

□ 업체명 : 라파즈한라시멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계(7-12월)	분석결과							
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kJ/kg)	분석 일자
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수처리오니	A	244	17.3	261.6	3.9	9.3	0.0	-	-	10/28
				B	54	0.3	12.5	0.0	0.0	0.0	-	-	7/20
		하수처리오니 (51-01-04)	하수처리오니	A	3,719	33.3	541.7	2.7	6.4	0.1	-	-	10/15
				B	90	22.1	154.8	1.6	11.2	0.0	-	-	7/18
				C	66	14.0	513.8	1.6	8.1	0.0	-	-	7/18
				D	1,081	52.5	385.6	3.1	9.7	0.0	-	-	7/18
				E	58	40.1	394.3	1.5	3.9	0.0	-	-	11/19
				F	257	22.9	400.9	1.3	8.7	0.0	-	-	10/23
				G	289	23.9	710.1	2.4	4.4	0.0	-	-	7/18
				H	10,539	19.8	411.7	1.0	4.0	0.9	-	-	10/15
				I	2,672	16.0	187.6	0.8	0.0	0.4	-	-	10/17
				J	1,342	16.5	196.3	1.0	2.4	0.0	-	-	10/15
				K	1,076	69.4	375.2	3.2	11.0	0.0	-	-	10/15
				L	840	47.6	324.5	2.1	7.7	0.2	-	-	10/23
				M	277	40.0	424.1	5.2	5.1	0.1	-	-	10/26
				N	430	30.0	747.0	6.5	7.5	0.0	-	-	10/16
				O	825	34.3	704.5	1.7	3.2	0.0	-	-	10/16
				P	108	31.4	372.5	1.4	2.9	0.4	-	-	7/18
	무기성오니류 (51-02-00)	무기성오니류 (51-02-02)	공정오니	A	154	10.0	26.1	0.3	7.2	0.2	-	-	7/20
				B	202	13.2	27.5	0.4	8.3	0.3	-	-	7/20
	정수처리오니 (51-02-03)	정수처리오니	정수처리오니	A	819	28.5	561.8	2.8	7.0	0.1	-	-	7/20
				A	21,997	12.2	25.9	0.2	13.1	0.5	-	-	12/24
	연소잔재물 (51-13-00)		석탄재	B	40,345	14.5	86.5	0.2	10.7	0.2	-	-	12/30
				C	4,577	11.6	29.8	0.2	11.4	0.1	-	-	9/5
				D	26,322	7.9	48.4	0.3	16.4	0.0	-	-	12/27
				A	19,943	15.4	29.8	0.0	2.6	0.1	-	-	12/29
	광재류 (51-04-00)	제강슬래그 (51-04-02) 기타 광재류 (51-04-03)	제강슬래그 기타 광재류	A	131	1.6	13.2	0.0	1.3	0.0	-	-	12/26
				B	7,404	9.0	11.4	0.0	1.8	0.0	-	-	12/29
폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	2,549	3.4	35.3	0.1	0.0	0.0	-	-	11/19	
			B	1,367	8.2	35.9	0.1	1.0	0.0	-	-	12/28	
			C	870	6.5	62.5	0.2	4.6	0.0	-	-	12/12	
			D	38,440	10.7	136.9	0.7	9.1	0.1	-	-	12/25	
폐석고 및 폐석회 (51-12-00)	폐석고 (51-12-01)	폐석고	A	958	0.9	25.2	0.1	26.9	0.0	-	-	12/4	
폐보드류 (51-32-00)		폐보드류	A	525	7.6	14.7	0.3	5.9	0.2	-	-	7/19	
그 밖의 폐기물 (51-99-00)		혼합철	A	978	15.0	70.6	2.2	0.6	0.0	-	-	12/29	
대체 원료	폐합성 고분자 화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	192	49.0	72.7	2.2	0.8	0.3	0.8	6,569	12/18
				B	92	61.6	53.7	3.3	0.0	0.0	1.1	5,776	9/4
				C	617	73.7	102.5	1.1	0.5	0.2	0.6	5,961	12/31
				D	2,428	59.8	95.1	7.1	1.9	0.2	0.6	4,512	12/25
				E	6,064	96.2	39.8	0.2	0.8	0.0	0.7	5,213	12/31
				F	1,586	42.3	92.6	8.3	0.0	0.2	1.1	5,396	12/25
				G	78	102.8	97.4	5.1	5.8	0.0	0.2	4,585	8/28
				H	2,398	54.9	733.1	0.9	0.0	0.1	0.8	5,024	7/17
				I	13,570	131.7	156.5	2.2	1.8	0.3	0.9	4,614	12/25
				J	12,596	47.5	45.0	0.3	0.0	0.1	0.6	4,693	12/25
				K	1,773	17.1	40.9	0.3	1.0	0.0	0.5	5,004	12/11
				L	283	118.5	287.7	0.9	2.3	0.0	1.1	5,503	12/11
				M	5,607	84.1	235.7	7.3	0.0	0.4	0.7	5,244	12/31
				N	418	49.4	432.7	4.0	0.0	0.2	1.4	4,843	12/25
				O	391	117.7	245.0	1.6	0.1	0.7	1.0	4,625	12/11
				P	782	31.8	38.7	0.4	1.1	0.0	0.9	4,663	11/20
				Q	108	195.5	720.5	1.3	3.3	0.1	0.9	5,344	11/27
				R	100	129.1	156.0	1.5	2.5	0.0	0.9	4,700	11/20
				S	2,603	74.7	166.7	2.7	2.2	0.2	0.7	4,827	9/4
				폐합성고무류 (51-03-02)	폐고무	A	4,951	23.1	135.0	0.4	1.4	0.0	1.1
	B	516	22.8			456.1	0.8	0.0	0.0	0.5	5,096	11/27	
	C	577	35.5			757.1	2.1	5.3	0.0	0.4	5,207	11/20	
	페타이어 (51-15-00)		페타이어	A	407	35.6	351.7	0.5	0.6	0.0	0.2	6,884	10/16
	폐목재류 (51-20-00)		폐목재류	A	705	21.2	23.1	0.9	0.0	0.0	0.5	4,236	12/31
	분진 (51-05-00)		중유회	A	1,772	5.1	34.1	0.1	11.1	0.1	0.3	6,205	8/16
				B	402	99.5	252.5	1.0	12.7	0.1	0.3	5,545	8/22