

재활용 폐기물 반입현황 (2014년 하반기)

□ 업체명 : 라파즈하라시멘트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계 (7~12월)	분석결과							
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수처리오니	A	321	21.1	328.1	21.8	11.5	1.0	-	-	11/24
				B	253	53.7	164.1	10.2	4.0	0.0	-	-	12/5
				C	1,726	4.5	36.0	1.8	5.2	0.0	-	-	11/26
		하수처리오니 (51-01-04)	하수처리오니	D	4,670	34.4	514.8	2.5	3.4	0.2	-	-	11/24
				E	123	24.9	255.8	1.3	4.1	-	-	-	11/24
				F	83	19.2	556.3	1.2	9.0	-	-	-	11/24
				G	975	3.2	295.9	31.5	21.5	0.2	-	-	11/24
				H	117	33.7	449.2	2.0	2.4	0.5	-	-	11/24
				I	283	28.8	379.7	1.2	5.0	0.0	-	-	11/28
				J	229	54.9	470.4	1.2	2.2	0.2	-	-	12/5
				K	10,397	12.8	374.7	0.8	5.0	0.0	-	-	11/21
				L	3,296	16.7	364.0	1.1	0.3	0.1	-	-	11/21
				M	3,034	11.7	164.0	1.2	5.3	0.1	-	-	11/21
				N	898	29.0	404.6	0.2	1.1	0.2	-	-	12/5
				O	869	73.7	164.1	11.2	7.0	0.0	-	-	12/5
	P	281	39.7	248.1	1.2	11.8	0.5	-	-	11/24			
	Q	720	20.6	124.0	7.6	8.6	0.6	-	-	11/26			
	R	633	33.7	449.2	2.0	2.4	0.5	-	-	11/24			
	무기성오니류 (51-02-00)	폐수처리오니 (51-02-01)	폐수처리오니	A	56,917	21.5	14.0	0.8	1.8	0.1	-	-	12/18
				B	8,524	12.3	10.2	0.2	1.1	0.0	-	-	12/18
		공정오니 (51-02-02)	공정오니	C	16,426	35.9	181.6	24.5	26.1	0.0	-	-	11/30
				D	13,082	13.3	9.5	0.3	11.7	0.0	-	-	10/29
	정수처리오니 (51-02-03)	정수처리오니	E	855	43.0	39.1	32.4	32.9	0.9	-	-	12/18	
	연소잔재물(51-13-00)		석탄재	A	35,825	7.6	24.6	0.2	11.4	0.3	-	-	10/10
				B	50,238	9.9	31.9	0.1	9.9	0.4	-	-	11/11
				C	42,512	10.4	39.6	0.4	11.7	0.0	-	-	11/6
	광재류 (51-04-00)	제강슬래그 (51-04-02)	제강슬래그	A	2,939	87.5	211.2	3.2	5.2	-	-	-	12/3
				B	287	0.3	21.4	1.8	2.5	-	-	-	12/15
		기타 광재류 (51-04-03)	기타 광재류	C	58	3.2	8.4	1.1	0.2	-	-	-	11/6
	폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	2,101	6.1	68.6	0.1	3.8	0.0	-	-	11/3
				B	21,166	32.1	82.9	0.5	2.5	-	-	-	10/19
				C	958	11.3	10.3	0.1	-	0.0	-	-	11/30
				D	6,360	2.8	155.5	0.9	6.6	-	-	-	10/22
E				2,945	2.7	9.1	-	1.1	0.0	-	-	12/20	
F				26,113	23.9	112.1	0.4	3.3	0.0	-	-	10/11	
폐석고 및 폐석회 (51-12-00)	폐석고 (51-12-01)	폐석고	A	235	109.0	12.6	1.6	5.5	0.0	-	-	12/10	
폐보드류 (51-32-00)		폐보드	A	1,545	48.7	7.1	2.6	1.3	0.1	-	-	12/10	
그 밖의 폐기물 (51-99-00)		혼합철	A	2,376	77.1	23.3	7.5	3.5	-	-	-	7/9	
보조 원료	폐합성고분자화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	10,528	26.9	74.1	0.9	7.6	0.1	0.3	4,571	8/20
				B	2,294	43.7	169.8	0.3	4.3	0.1	0.4	5,174	10/29
				C	7,698	120.7	87.7	0.4	1.3	0.0	0.9	4,560	11/19
				D	5,527	99.9	178.3	3.9	4.7	0.1	0.7	5,216	11/12
				E	12,893	49.8	56.8	0.7	4.0	0.0	1.2	5,521	10/22
				F	878	86.1	298.9	0.9	4.3	-	0.8	5,981	11/19
				G	5,707	36.9	66.6	0.3	6.2	-	0.6	4,534	11/19
				H	388	9.9	63.9	0.2	-	-	0.1	4,869	9/24
				I	1,385	108.8	530.2	1.3	-	0.0	0.5	4,554	10/15
				J	2,491	93.9	45.9	0.6	3.4	0.0	0.5	6,121	11/19
				K	4,491	51.5	501.7	0.5	-	0.1	0.6	4,571	10/22
				L	156	124.5	562.5	1.3	10.3	0.5	0.5	4,566	10/15
				M	2,136	78.0	453.9	4.1	1.4	0.1	1.2	5,216	10/29
				N	1,765	18.7	302.2	0.2	-	-	0.2	5,833	11/19
				O	264	141.0	90.4	0.5	-	0.4	0.8	4,519	10/22
				P	643	39.2	654.6	0.9	-	-	0.2	6,166	10/22
				Q	5,298	13.5	24.5	-	-	-	0.7	5,624	10/29
				R	20	11.3	81.8	0.3	8.9	0.0	0.1	6,710	10/22
	폐목재류 (51-20-00)		폐목재	A	745	1.0	15.4	0.1	1.1	-	0.4	4,391	11/12
				B	224	8.8	11.7	1.5	1.3	0.0	0.3	4,058	11/12
				C	1,140	21.2	22.7	0.6	1.5	0.1	0.3	3,563	9/17
				D	23	5.4	-	0.1	-	-	0.3	4,045	9/24
				E	216	0.1	12.0	0.9	0.3	-	0.2	3,792	11/19
				F	3,854	19.9	246.8	0.4	1.3	0.0	0.2	4,318	11/19
분진 (51-05-00)		중유회	A	266	26.3	134.7	0.3	6.2	0.0	0.2	5,895	11/28	
			B	795	95.4	248.0	0.5	4.7	0.0	0.4	5,403	11/28	