

재활용 폐기물 반입현황 (2015년 상반기)

□ 업체명 : 라파즈하라스먼트(옥계공장)

구분	종류			공급자	반입량 (톤) 누계(1~6월)	분석결과									
	대분류	중분류	세분류			Pb (mg/kg)	Cu (mg/kg)	Cd (mg/kg)	As (mg/kg)	Hg (mg/kg)	Cl (%)	저위발열량 (kcal/kg)	분석 일자		
대체 원료	유기성오니류 (51-01-00)	폐수처리오니 (51-01-01)	폐수오니	A	2,184	13.0	256.4	1.6	15.5	-	-	-	3/27		
				B	198	7.2	268.1	3.1	16.7	0.0	-	-	3/27		
				C	97	9.4	241.7	2.7	20.2	0.1	-	-	3/27		
				D	402	4.3	274.8	4.7	43.2	0.0	-	-	3/27		
		하수처리오니 (51-01-04)	하수오니	A	1,557	3.0	48.2	2.0	7.0	-	-	-	1/21		
				A	3,940	31.3	540.4	1.9	5.0	0.6	-	-	1/21		
				B	139	20.1	571.6	6.1	7.9	0.2	-	-	1/21		
				C	87	24.2	229.1	1.7	9.1	0.1	-	-	1/21		
				D	1,358	13.0	256.4	1.6	15.5	0.0	-	-	1/21		
				E	218	19.8	388.3	0.6	5.8	0.8	-	-	1/21		
				F	348	17.1	482.1	0.8	4.2	0.3	-	-	1/21		
				G	296	10.1	569.1	0.7	-	0.2	-	-	4/3		
				H	11,711	10.3	423.1	1.0	9.6	0.8	-	-	1/21		
				I	2,854	26.0	161.9	0.8	3.8	0.2	-	-	1/21		
				J	2,288	12.8	436.9	1.3	9.9	0.2	-	-	3/27		
				K	1,375	26.7	511.4	0.8	8.7	0.9	-	-	1/21		
				L	1,358	24.2	284.7	1.9	12.3	0.1	-	-	3/27		
				M	1,182	31.1	217.3	2.2	11.0	0.1	-	-	1/21		
	N	377	39.9	504.5	5.8	9.2	1.4	-	-	1/29					
	O	1,635	24.5	532.8	6.9	11.4	1.0	-	-	4/3					
	P	725	31.3	534.4	1.4	0.7	1.4	-	-	1/29					
	무기성오니류 (51-02-00)	폐수처리오니 (51-02-01)	폐수오니	A	73,046	14.4	13.6	0.5	2.9	0.1	-	-	1/7		
				B	10,145	10.1	14.2	0.2	1.5	-	-	-	1/21		
		공정오니 (51-02-02)	공정오니	A	12,601	10.4	6.9	0.1	9.8	0.1	-	-	3/26		
				A	755	7.3	20.8	2.2	4.3	0.1	-	-	1/21		
	정수처리오니 (51-02-03)	정수오니	A	115	5.8	2.9	0.4	11.0	-	-	-	1/21			
			A	115	5.8	2.9	0.4	11.0	-	-	-	1/21			
	광재류 (51-04-00)	제강 슬래그 (51-04-02)	제강 슬래그	A	9,951	-	8.0	0.5	3.5	0.0	-	-	3/30		
		기타 광재류 (51-04-03)	기타 광재류	A	401	4.0	51.8	1.7	3.4	0.0	-	-	6/24		
	폐주물사 및 폐사 (51-06-00)	폐주물사 (51-06-01)	폐주물사	A	5,030	3.9	57.0	0.4	6.4	-	-	-	6/10		
				B	29,556	3.9	62.2	0.4	7.4	-	-	-	6/12		
				C	1,440	4.0	24.2	0.2	1.7	0.0	-	-	5/28		
				D	1,416	2.4	69.5	0.3	6.2	-	-	-	1/13		
				E	11,261	11.3	71.0	0.3	1.6	0.1	-	-	3/25		
	폐석고 및 폐석회 (51-12-00)	폐석고 (51-12-01)	폐석고	A	208	43.0	379.1	4.6	2.9	1.7	-	-	1/19		
	연소잔재물 (51-13-00)	석탄재	A	19,114	10.0	25.1	0.5	16.6	0.4	-	-	-	1/5		
			B	53,900	8.4	33.3	0.2	6.5	0.4	-	-	-	1/17		
			C	20,347	11.5	27.5	0.1	15.8	0.3	-	-	-	1/25		
	폐보드류 (51-32-00)		폐보드	A	326	51.1	98.0	5.4	3.7	0.2	-	-	1/19		
	그 밖의 폐기물 (51-99-00)		혼합철	A	302	91.2	25.7	6.6	7.3	0.3	-	-	4/28		
	보조 원료	폐합성고분자화합물 (51-03-00)	폐합성수지류 (51-03-01)	폐합성수지	A	5,599	36.3	54.8	2.0	1.1	0.4	0.6	5,007	4/7~4/13	
					B	8	79.6	217.2	5.7	2.5	0.1	1.3	5,910	6/30~7/6	
C					3,391	19.6	68.4	0.5	2.0	-	0.5	5,117	4/16~4/20		
D					3,572	174.1	350.9	1.1	-	0.0	0.5	4,864	3/24~3/30		
E					4,112	101.7	382.4	5.4	1.8	0.6	1.2	5,093	2/17~2/23		
F					1,310	68.7	98.4	2.6	1.7	-	0.8	4,632	4/21~4/27		
G					1,773	56.0	515.4	0.2	1.1	0.0	1.1	6,704	3/24~3/30		
H					3,377	81.7	191.1	3.9	1.6	0.4	1.3	6,420	4/7~13		
I					6,770	68.4	158.4	2.0	2.5	1.0	0.9	5,857	4/7~13		
J					2,054	101.3	264.4	1.1	5.5	-	0.9	4,987	3/24~3/30		
K					358	85.1	197.2	1.2	2.1	0.1	0.5	5,258	5/26~6/1		
L					3,346	53.5	119.6	0.7	2.7	-	0.9	5,936	3/24~3/30		
M					286	80.8	228.1	2.1	1.8	0.2	0.1	6,691	6/2~6/8		
N					340	55.8	81.1	2.5	1.4	0.0	1.1	6,427	4/7~13		
O					2,720	50.3	80.3	0.3	9.3	0.0	0.5	5,495	1/13~1/19		
P					4,110	138.5	119.0	4.0	5.3	0.1	0.7	4,752	1/13~1/19		
Q					875	139.7	670.2	5.6	-	0.0	0.7	4,708	3/24~3/30		
R					3,737	64.7	90.0	0.5	0.1	0.2	0.9	5,402	4/7~13		
S					53	70.1	207.6	1.8	3.2	0.7	0.8	5,109	6/2~8		
T					532	76.0	490.5	1.1	7.9	0.8	0.3	4,630	3/10~3/16		
U					1,322	118.5	345.7	4.0	0.6	0.0	0.8	5,070	4/16~20		
V					552	18.1	253.8	0.1	-	0.0	0.0	4,619	3/24~3/30		
폐합성고무류 (51-03-02)					폐고무	A	53	27.1	89.7	0.2	3.6	0.2	0.2	6,145	2/10~16
						B	2,323	57.1	59.6	0.3	8.7	0.2	0.3	6,811	3/3~9
		C	313	11.7		41.0	-	1.0	0.1	0.6	6,638	4/7~13			
		D	59	31.9		275.5	0.6	2.6	-	0.1	7,708	1/13~1/19			
폐목재류 (51-20-00)		폐목재류	A	303	15.7	13.5	1.4	0.9	0.0	0.4	4,603	3/3~3/9			
			B	910	20.2	16.7	1.8	0.8	0.0	0.5	3,973	3/31~4/6			
			C	71	11.6	44.7	0.6	1.1	-	0.3	4,134	3/24~3/30			
			D	814	-	10.6	0.1	-	0.0	0.3	4,413	3/31~4/6			
			E	11,292	21.4	18.3	1.1	1.5	0.1	0.3	3,874	3/31~4/6			
			F	2,676	20.5	17.9	1.4	-	0.0	0.5	3,893	3/31~4/6			
분진 (51-05-00)		중유회	A	715	13.4	64.1	0.1	10.8	-	0.2	6,053	4/25			
	B		1,174	4.9	29.8	-	9.6	0.0	0.2	7,363	3/25				